

Anisotropic magnons in the layered honeycomb ferromagnet CrSiTe₃T. J. Williams¹**ISIS Pulsed Neutron & Muon Source, STFC Rutherford Appleton Laboratory, Harwell Campus,
Didcot OX11 0QX, United Kingdom*D. L. Abernathy² and M. D. Lumsden²*Neutron Scattering Division, Neutron Sciences Directorate, Oak Ridge National Laboratory,
Oak Ridge, Tennessee 37831, USA*J.-Q. Yan² and A. D. Christianson²*Materials Science & Technology Division, Physical Sciences Directorate, Oak Ridge National Laboratory,
Oak Ridge, Tennessee 37831, USA* (Received 23 February 2026; revised 28 July 2026; accepted 17 August 2026; published 17 September 2026)

Recent experimental and theoretical studies have suggested a possible Dirac magnon gap in the two-dimensional ferromagnetic semiconductor CrSiTe₃. Detailed neutron scattering measurements were performed to shed light on the existence of the magnon gap, and suggest that the gap is very small or nonexistent, with previous measurements being complicated by experimental factors. During these measurements, it was found that the out-of-plane couplings could explain the usual property of the increase in the magnetic transition temperature when CrSiTe₃ is exfoliated to monolayers. Furthermore, the material was shown to have anisotropic magnons along the out-of-plane direction, through the proposed Dirac point. We speculate that this is due to an exchange anisotropy, though Kitaev-like interactions alone cannot explain the spectra.

DOI: [10.1103/c7bd-ghcb](https://doi.org/10.1103/c7bd-ghcb)**I. INTRODUCTION**

Two-dimensional (2D) magnetic materials have recently emerged as a vibrant platform for exploring novel quantum phenomena and for advancing next-generation spintronic devices [1,2]. Among these materials, chromium-based trichalcogenides, such as CrSiTe₃, have attracted particular interest due to their layered van der Waals structure, intrinsic ferromagnetism, and strong spin-orbit coupling [3,4]. CrSiTe₃ is a semiconducting ferromagnet that retains long-range magnetic order down to the monolayer limit, making it a promising candidate for studying low-dimensional magnetism and collective spin excitations. Among the promising properties of CrSiTe₃ is the possibility of Dirac magnons [5]. Analogous to Dirac fermions in graphene, Dirac magnons represent a topologically nontrivial excitation characterized by linear band crossings at discrete momentum points in the Brillouin zone. The existence of Dirac magnons in honeycomb-lattice magnets opens up new avenues for exploring bosonic analogs of topological phases, including magnonic analogues of the quantum Hall and spin Hall

effects [6]. The identification and control of such excitations in real materials is a critical step toward realizing topological magnonics, where robust, low-dissipation spin transport could be achieved via edge modes protected by symmetry.

In this work, we reinvestigate the magnons of CrSiTe₃, focusing on the possible emergence of Dirac magnons due to its honeycomblake arrangement of Cr atoms and underlying magnetic interactions. This sheds light on the role of anisotropy, exchange coupling, and Dzyaloshinskii-Moriya (DM) interactions in shaping the topological character of the magnon bands.

Previous work by our group on single crystals of CrSiTe₃ has shown a small distortion of the Te octahedra along the *c* axis that result in a small easy-axis anisotropy [4]. This was confirmed using elastic and inelastic neutron scattering measurements on single crystals of CrSiTe₃ that found a small spin gap of 0.075 meV that gives rise to the ferromagnetic ground state, with moments oriented parallel to *c* [7]. The temperature dependence of the magnetic Bragg peak shows a critical exponent that is very close to the 2D Ising value, and diffuse scattering around the magnetic Bragg peaks provides further evidence of quasi-2D behavior that persists well above the ordering temperature. Time-of-flight (TOF) and triple-axis inelastic neutron scattering measurements performed on single crystals aligned in the [*H* 0 *L*] scattering plane [7] demonstrate well-ordered spin waves below *T_C*, with in-plane diffuse spin correlations persisting up to room temperature [7]. Modeling and fits of the spin waves were done with a Hamiltonian that included three Heisenberg in-plane exchange terms and one

*Contact author: travis.williams@stfc.ac.uk

exchange along the c axis, all of which were found to be ferromagnetic, in addition to the single-ion term [7]. This work showed that the moments were only weakly coupled along the c axis, with the dominant exchange terms lying in the plane, consistent with the diffuse elastic and inelastic scattering that showed correlations within the ab plane that persist well above T_C .

More recent neutron spectroscopy measurements have suggested the existence of a Dirac magnon gap at the K point in CrSiTe_3 [8], which would give rise to corresponding in-gap topological edge states. This gap was attributed to the existence of a Dzyaloshinskii-Moriya (DM) interaction of 0.12 meV between magnetic ions with broken inversion symmetry, while the remaining terms in the Hamiltonian comprised two in-plane exchange terms, J_{ab1} and J_{ab2} , and two out-of-plane terms, J_{c1} and J_{c2} . The differences in the Hamiltonian and the sizable DM term suggested a reexamination of our previous neutron data, as well as the need to perform additional measurements in the $[H H L]$ scattering plane to examine the magnon dispersions around the Dirac (K) point.

The work in Ref. [8] did not describe any corrections due to instrumental resolution, which may alter the size of the gap and thus the value of the DM term. Additionally, the triple-axis measurements in that work did not account for a $k_i \rightarrow k_i$ spurion arising from the (0 0 3) nuclear Bragg peak. This is an unusual spurion, as it involves coherent scattering from the monochromator and sample, but incoherent scattering from the Pyrolytic graphite (PG) analyzer. Although incoherent scattering from PG is very weak, the (0 0 3) Bragg peak is the most intense nuclear peak, and this spurion should be of the same order of magnitude as the intensity of the inelastic scattering from the magnons. On a triple-axis instrument, this spurion appears at (0.3 0.3 6) with an energy transfer of 8 meV, which is very close to the location of the proposed Dirac magnon gap. This provided additional motivation to perform measurements that could investigate this as a source of error in measuring the magnitude of the gap.

II. EXPERIMENTAL DETAILS

CrSiTe_3 single crystals were grown using a self-flux technique, as previously reported [4]. CrSiTe_3 is rhombohedral, crystallizing in the space group $R\bar{3}$. Susceptibility and neutron diffraction measurements showed a ferromagnetic transition at $T_C = 33(1)$ K [4,7], in agreement with other reports [9,10]. In order to study the existence of a gap in the magnon spectrum and the impact of experimental resolution, inelastic neutron scattering measurements were performed at the HB-3 thermal triple-axis spectrometer of the High-Flux Isotope Reactor, as well as the ARCS time-of-flight spectrometer at the Spallation Neutron Source of the Oak Ridge National Laboratory.

A single crystal of mass 3.7 g was aligned with a $[H H L]$ scattering plane for the ARCS and HB3 measurements. The ARCS measurements were performed in a closed-cycle refrigerator with a base temperature of 4.0 K. Measurements were performed in a high-flux configuration with fixed incident energies of 30 and 15 meV. The HB3 measurements were also performed in a closed-cycle refrigerator with a base temperature of 4.0 K using fixed final energies of 14.7 and

TABLE I. The out-of-plane exchange constants calculated from the neutron scattering data measured along $(\frac{1}{2} \frac{1}{2} L)$. While the nearest-neighbor exchange is antiferromagnetic, the next-nearest-neighbor exchanges dominates due to a greater number of J_{c2} bonds. This results in the observed ferromagnetic ground state, while the competition from these two interactions may drive the reduction in T_C from the monolayer.

Exchange	No. bonds	Vector	Distance	Value (meV)
J_{ab1}	3	$(\frac{1}{3} \frac{2}{3} 0)$	3.907 Å	-1.63(33)
J_{ab2}	6	$(1 0 0)$	6.768 Å	-0.010(-)
J_{ab3}	3	$(\frac{2}{3} -\frac{2}{3} 0)$	7.814 Å	-0.285(-)
J_{c1}	1	$(0 0 \frac{1}{3})$	7.007 Å	0.080(9)
J_{c2}	6	$(\frac{2}{3} \frac{1}{3} \frac{1}{3})$	8.700 Å	-0.077(2)

5.5 meV. PG(002) monochromator and analyzer crystals were used with PG filters, and the collimation was 48'-40'-40'-120'. Where mentioned, our previous measurements on CrSiTe_3 aligned in the $[H 0 L]$ scattering plane were reported in Ref. [7].

III. DIRAC MAGNON GAP

To investigate the nature of a Dirac magnon gap at the K point, measurements were performed on the ARCS thermal time-of-flight spectrometer. Following the work of Ref. [8], which ascribed the magnon gap to a second nearest-neighbor DM interaction, our measurements were performed with the crystal aligned in the $[H H L]$ scattering plane, focused on reciprocal space directions of $(\frac{1}{3} \frac{1}{3} L)$, which passes through the K point, and $(\frac{1}{2} \frac{1}{2} L)$, where the value of the DM interaction does not contribute to the magnon dispersion. This allows for a separation of the Heisenberg interactions along the c axis with a possible DM interaction.

The measured bandwidth along $(\frac{1}{2} \frac{1}{2} L)$ was used to determine the exchange interactions along the c axis. This was measured to be 0.61 meV, slightly smaller than 0.73 meV from our previous measurement [7], taken along a different reciprocal space direction. Using the single-ion anisotropy, $D_{ij} = 0.0252$ meV and the geometry of the $R\bar{3}$ stacking, the relationship between J_{c1} and J_{c2} can be constrained. There is only one nearest-neighbor (J_{c1}) bond along c , but there are six J_{c2} bonds. When combined with the phase factor of 1.5 and fitting to the measured bandwidth, we can constrain $J_{c1} + 9J_{c2} = -0.61$ meV. Additional interactions out of the plane such as J_{c3} result in overparametrizing the data and do not provide a meaningful improvement in the fit. A fit to the dispersion gives the value of these interactions listed in Table I.

The opposite sign of the two interactions indicates significant frustration in bulk samples along the c axis, while the larger number of J_{c2} bonds relative to J_{c1} means that the ferromagnetic interaction dominates and gives rise to the ferromagnetic ground state. This difference in the sign of the interaction also offers an explanation for the low T_C considering the intraplane interactions that persist up to room temperature [7] and that the ordering transition of CrSiTe_3 increases as the material is exfoliated to thin films and




FIG. 1. (a) A line cut through the K point by integrating $(\frac{1}{3} \pm 0.05 \frac{1}{3} \pm 0.05 - 6 \pm 0.1)$ and $\Delta E = 0.25$ meV using the data collected on ARCS. The data were then fit to the Hamiltonian described in the text, including the DM term. The fit value for the DM term was 0.115(3) meV, in good agreement with Ref. [8]. (b) When the procedure done in the top panel was repeated for integrating different Q volumes around the K point, the fit value of the DM term was found to monotonically decrease with the integration range. The fits did not converge for volumes with $\delta < 0.025$ r.l.u.

monolayers [11], relieving the long-range interlayer frustration. While the nearest-neighbor interaction along the c axis is antiferromagnetic, the J_{c2} interaction is of comparable strength and the larger multiplicity stabilizes the 3D ferromagnetism in the material. This has implications for the nature of the ordering of the material in the presence of lattice distortions, in agreement with theoretical predictions for CrSiTe₃ under in-plane strain [12]. Devices and heterostructures where CrSiTe₃ is placed on a substrate will similarly be subjected to lattice strain that can affect the degree of magnetic frustration [13].

To look for the presence of a magnon gap, we looked at the constant- Q cut at the K point $= (\frac{1}{3} \frac{1}{3} -6)$, shown in Fig. 1(a). The spurion described above will not be present in time-of-flight data, but is subject to other resolution effects, as described below. To create this cut, the data were integrated to cover the volume of Q space contained in $(\frac{1}{3} + \delta, \frac{1}{3} + \delta,$

$-6 + 2\delta)$ with $\delta = 0.05$ r.l.u. The data were fit to the following Hamiltonian:

$$H = J_{ab1} \sum_i \vec{S}_i \cdot \vec{S}_{i+1} + J_{ab2} \sum_i \vec{S}_i \cdot \vec{S}_{i+2} + J_{c1} \sum_i \vec{S}_i \cdot \vec{S}_{i+3} + J_{ab3} \sum_i \vec{S}_i \cdot \vec{S}_{i+4} + J_{c2} \sum_i \vec{S}_i \cdot \vec{S}_{i+5} - D_{ij} \sum_{i < j} \vec{S}_i \times \vec{S}_j, \quad (1)$$

where the exchanges out to the sixth-nearest neighbor are included. This Hamiltonian follows the work of Ref. [7], where a third-nearest-neighbor term, J_{ab3} , was needed to capture the spin-wave dispersions in the plane, and the work of Ref. [8], where a second out-of-plane exchange, J_{c2} , and the DM term, D_{ij} , were included.

In order to fit the cut in Fig. 1(a) to Eq. (1), the values for J_{c1} and J_{c2} obtained above were used, along with the values obtained from our previous work [7]. The value of the nearest-neighbor interaction was fit along with the DM term, and this gave a value for the DM interaction of 0.115(3) meV. This is in excellent agreement with the previous work in Ref. [8], which found a value of $D = 0.12$ meV. The values of the parameters are summarized in Table I. As we discuss in the following paragraph, this demonstrates reproducibility of the data, but the existence of a DM interaction may be more complex.

Recent work on another Cr honeycomb material, CrI₃, has demonstrated that an apparent magnon gap was likely overestimated due to finite instrumental resolution and the data integration volume used in the analysis [14]. To perform a similar analysis on CrSiTe₃, the integration volume defined by δ was decreased from 0.2 r.l.u. and fitting the data in the same manner as described above to obtain a value for the DM interaction. The results are shown in Fig. 1(b) and show that the resulting value of the DM interaction decreases monotonically with the integration volume, as was observed in CrI₃. For values of $\delta < 0.025$ r.l.u., the fits did not converge, so it is unclear whether the DM term vanishes or is present, but much smaller than reported.

IV. INSTRUMENTAL RESOLUTION

To make more quantitative conclusions about the DM interaction and the effect of instrumental resolution, measurements were also performed on the thermal triple-axis spectrometer HB3. Constant- Q measurements at the K point $(\frac{1}{3} \frac{1}{3} 3)$ were performed with fixed final energies of $E_f = 5.5$ and 14.7 meV. To remove spurious scattering and other sources of background, a background was measured by driving the PG analyzer to zero scattering angle and performing the identical constant- Q scan. This removes coherent scattering from the analyzer, but preserves the incoherent scattering that gives rise to the spurion at (0.3, 0.3, 3) and 8 meV. The background-subtracted data were fit to the Hamiltonian described in Eq. (1), with the J_{c1} and J_{c2} values determined earlier and the DM term fixed to zero. This Hamiltonian was convoluted with the instrumental resolution calculated with reslib [15] and the corresponding fit is shown in Fig. 2.

The data are seen to be consistent with the absence of a DM interaction, though it does not rule out a small term.




FIG. 2. A constant- Q scan at the K point on the HB3 thermal triple-axis spectrometer. A background scan was also performed using the same configuration, but driving the analyzer flat. This removes coherent scattering from the analyzer, but preserves the incoherent signal that is a source of spurious scattering. The background-subtracted data are shown, where the solid line is a fit to the Hamiltonian with zero DM term, and convoluted with the instrumental resolution.

Fitting this data with a nonzero DM term did not converge due to overparameterization from the in-plane interactions, but it was seen that the data were not consistent with a DM term of the magnitude reported in Ref. [8]. This suggests that the behavior of CrSiTe_3 is likely similar to that of CrI_3 [14], CrBr_3 [16], CrCl_3 [17], and other related materials that may possess a very small gap. The nature of the interactions is more complicated than the Hamiltonian used, as it does not account for the anisotropic magnons that were observed, described in the section below.

V. ANISOTROPIC MAGNONS

The ARCS data showing the dispersions along the $(\frac{1}{2} \frac{1}{2} L)$ direction are shown in Fig. 3(a). Simulation of this spin-wave spectrum were done using SPINW [18] utilizing the Hamiltonian described above. Along this direction, the spin-wave spectrum is not sensitive to the presence of a DM interaction, though for these calculations the DM interaction is fixed to zero. The data for the $(\frac{2}{3} \frac{2}{3} L)$ direction are shown in Fig. 3(d). It was observed that the spectrum along this direction is not symmetric about $L=0$ (L is not equivalent to $-L$), while the simulated data were symmetric.

This anisotropic magnon dispersion is allowed by the crystal symmetry since there is no mirror plane along the c axis. However, the anisotropy cannot be reproduced with the linear




FIG. 3. (a) Spin waves measured along the $(\frac{1}{2} \frac{1}{2} L)$ direction, where there is no contribution from a DM term. This data were used to constrain the fits to the out-of-plane exchange constants. (b) Spin-wave simulations of the $(\frac{1}{2} \frac{1}{2} L)$ dispersion with the Kitaev interaction described in the text. (c) The data along $(\frac{1}{2} \frac{1}{2} L)$ at the top of the band ($\Delta E = 10.5$ meV) overlaid with simulations using a purely Heisenberg Hamiltonian and no DM interaction (solid line), and the same Hamiltonian, but with the nearest-neighbor in-plane interaction being a Kitaev interaction (dashed line). Both agree well with the data, as this reciprocal space direction is not sensitive to changes in these parameters. (d) Spin waves measured along the $(\frac{2}{3} \frac{2}{3} L)$ direction, where the dispersion is seen to be anisotropic relative to $L=0$. (e) The simulations along the panel (a) direction including the Kitaev interaction. This distorts the spin-wave spectrum and produces an anisotropy along the L direction. (f) The data overlaid with the Heisenberg and Kitaev exchange simulations along the top of the band ($\Delta E = 10$ meV). This shows that the anisotropy produced by the Kitaev term does not change the band minima/maxima, fundamentally different from the spin-wave anisotropy observed in the data.

spin-wave theory (LSWT) calculations in `spinw`, including the introduction of a DM interaction. Using the software package `SUNNY` [19], the introduction of a Kitaev interaction along the nearest-neighbor in-plane exchange (J_{ab1}) does not change the symmetry of the bands, but it does produce some anisotropy in the spin-wave intensity. This anisotropy appears in the middle of the band, which does not match the experimental data. In the data, the intensity remains at the extrema of the band, where the data are anisotropic, but the model is not. Figures 3(b) and 3(e) show the simulated data along these directions with the inclusion of this Kitaev interaction. To highlight the difference between the data and simulations, Figs. 3(c) and 3(f) show line cuts along these two directions at the top of the spin-wave band. This shows that for the $(\frac{2}{3}, \frac{2}{3})L$ direction, the introduction of the anisotropic Kitaev exchange does not change the L symmetry of the band maxima and minima. Other exchanges, including in-plane DM interactions, biquadratic exchange, and other Kitaev terms, were introduced to attempt to explain the data, but could not explain the observed asymmetric magnons. It may indicate that some other form of exchange anisotropy is responsible for this behavior, but this is an open question.

This anisotropy is not present along any other measured reciprocal space direction. It is also an open question as to why the $K-H-K'$ direction is unique in this regard, especially when compared to other reciprocal space directions, such as $\Gamma-A-\Gamma'$.

VI. CONCLUSIONS

We have reexamined the magnon dispersions in CrSiTe_3 in light of the possible emergence of Dirac magnons. Neutron spectroscopy measurements have demonstrated the importance of the second-nearest-neighbor out-of-plane interaction, J_{c2} , in stabilizing the long-range order. The frustration of J_{c1} and J_{c2} may explain the increase in the magnetic transition temperature when CrSiTe_3 is exfoliated to monolayers or is

subjected to in-plane strain. A careful study of the magnon dispersion around the K point suggests that the observed gap appears to be enhanced due to resolution effects and spurious scattering. If there is a DM term present in this material, it is likely much smaller than previously reported.

Finally, an anisotropic magnon dispersion was observed along the $(\frac{2}{3}, \frac{2}{3})L$ direction, which encompasses the K point, with no anisotropy observed for other reciprocal lattice directions. This anisotropy has not been explained with Kitaev interactions, but simulations of the data using a Kitaev term have shown anisotropic spectral weight, suggesting that the anisotropy observed in the data may arise due to other anisotropic exchange. Determining the form of this exchange interaction may shed further light on the Hamiltonian and the nature of any gapped excitations or Dirac magnons.

ACKNOWLEDGMENTS

This research used resources at the High Flux Isotope Reactor and Spallation Neutron Source, a DOE Office of Science User Facility operated by the Oak Ridge National Laboratory. The beam time was allocated to HB3 on proposal number IPTS-29984.1 and to ARCS on proposal number 31183.1. The United States Government retains and the publisher, by accepting the article for publication, acknowledges that the United States Government retains a nonexclusive, paid-up, irrevocable, worldwide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes. The Department of Energy will provide public access to these results of federally sponsored research in accordance with the DOE Public Access Plan.

DATA AVAILABILITY

The data that support the findings of this article are openly available [20]; embargo periods may apply.

-
- [1] G. R. Bhimanapati, Z. Lin, V. Meunier, Y.-W. Jung, J. J. Cha, S. Das, D. Xiao, Y.-W. Son, M. S. Strano, V. R. Cooper, L. Liang, S. G. Louie, E. Ringe, W. Zhou, B. G. Sumpter, H. Terrones, F. Xia, Y. Wang, J. Zhu, D. Akinwande, *et al.*, Recent advances in two-dimensional materials beyond graphene *ACS Nano* **9**, 11509 (2015).
 - [2] M. V. Milošević and D. Mandrus, 2D quantum materials: Magnetism and superconductivity, *J. Appl. Phys.* **130**, 180401 (2021).
 - [3] P. Liu, Y. Zhang, K. Li, Y. Li, and Y. Pu, Recent advances in 2D van der Waals magnets: Detection, modulation, and applications, *iScience* **26**, 107584 (2023).
 - [4] L. D. Casto, A. J. Clune, M. O. Yokosuk, J. L. Musfeldt, T. J. Williams, H. L. Zhuang, M. W. Lin, K. Xiao, R. G. Hennig, B. C. Sales, J.-Q. Yan, and D. Mandrus, Strong spin-lattice coupling in CrSiTe_3 , *APL Mater.* **3**, 041515 (2015).
 - [5] S. S. Pershoguba, S. Banerjee, J. C. Lashley, J. Park, H. Ågren, G. Aeppli, and A. V. Balatsky, Dirac magnons in honeycomb ferromagnets, *Phys. Rev. X* **8**, 011010 (2018).
 - [6] Y.-S. Lu, J.-L. Li, and C.-T. Wu, Topological phase transitions of Dirac magnons in honeycomb ferromagnets, *Phys. Rev. Lett.* **127**, 217202 (2021).
 - [7] T. J. Williams, A. A. Aczel, M. D. Lumsden, S. E. Nagler, M. B. Stone, J.-Q. Yan, and D. Mandrus, Magnetic correlations in the quasi-two-dimensional semiconducting ferromagnet CrSiTe_3 , *Phys. Rev. B* **92**, 144404 (2015).
 - [8] F. Zhu, L. Zhang, X. Wang, F. J. dos Santos, J. Song, T. Mueller, K. Schmalzl, W. F. Schmidt, A. Ivanov, J. T. Park, J. Xu, J. Ma, S. Lounis, S. Blügel, Y. Mokrousov, Y. Su, and T. Brückel, Topological magnon insulators in two-dimensional van der Waals ferromagnets CrSiTe_3 and CrGeTe_3 : Toward intrinsic gap-tunability, *Sci. Adv.* **7**, eabi7532 (2021).
 - [9] V. Carteaux, F. Moussa, and M. Spiesser, 2D Ising-like ferromagnetic behaviour for the lamellar $\text{Cr}_2\text{Si}_2\text{Te}_6$ compound: A neutron scattering investigation, *Europhys. Lett.* **29**, 251 (1995).
 - [10] K. Yang, H. Wu, Z. Li, C. Ran, X. Wang, F. Zhu, X. Gong, Y. Liu, G. Wang, L. Zhang, X. Mi, A. Wang, Y. Chai, Y. Su, W.

- Wang, M. He, X. Yang, and X. Zhou, Spin-phonon scattering-induced low thermal conductivity in a van der Waals layered ferromagnet $\text{Cr}_2\text{Si}_2\text{Te}_6$, *Adv. Func. Mater.* **33**, 2302191 (2023).
- [11] M.-W. Lin, H. L. Zhuang, J. Q. Yan, T. Z. Ward, A. A. Poretzky, C. M. Rouleau, Z. Gai, L. Liang, V. Meunier, B. G. Sumpter, P. Ganesh, P. R. C. Kent, D. B. Geohegan, D. Mandrus, and K. Xiao, Ultrathin nanosheets of CrSiTe_3 : A semiconducting two-dimensional ferromagnetic material, *J. Mater. Chem. C* **4**, 315 (2016).
- [12] N. Sivadas, M. W. Daniels, R. H. Swendsen, S. Oakamoto, and D. Xiao, Magnetic ground state of semiconducting transition-metal trichalcogenide monolayers, *Phys. Rev. B* **91**, 235425 (2015).
- [13] Q. Pei, X. Wang, J. Zou, and W. Mi, Efficient band structure modulations in two-dimensional $\text{MnPSe}_3/\text{CrSiTe}_3$ van der Waals heterostructures, *Nanotechnology* **29**, 214001 (2018).
- [14] S.-H. Do, J. A. M. Paddison, G. Sala, T. J. Williams, K. Kaneko, K. Kuwahara, A. F. May, J.-Q. Yan, M. A. McGuire, M. B. Stone, M. D. Lumsden, and A. D. Christianson, Gaps in topological magnon spectra: Intrinsic versus extrinsic effects, *Phys. Rev. B* **106**, L060408 (2022).
- [15] A. Zheludev, *ResLib 3.4* (Oak Ridge National Laboratory, Oak Ridge, TN, 2007).
- [16] S. E. Nikitin, B. Fåk, K. W. Krämer, T. Fennell, B. Normand, A. M. Läuchli, and Ch Rüegg, Thermal evolution of Dirac magnons in the honeycomb ferromagnet CrBr_3 , *Phys. Rev. Lett.* **129**, 127201 (2022).
- [17] L. Chen, M. B. Stone, A. I. Kolesnikov, B. Winn, W. Shon, P. Dai, and J.-H. Chung, Massless Dirac magnons in the two dimensional van der Waals honeycomb magnet CrCl_3 , *2D Mater.* **9**, 8138 (2025).
- [18] S. Toth and B. Lake, Linear spin wave theory for single-Q incommensurate magnetic structures, *arXiv/cond-mat:1402.6069*.
- [19] D. Dahlbom, H. Zhang, C. Miles, S. Quinn, A. Niraula, B. Thipe, M. Wilson, S. Matin, H. Mankad, S. Hahn, D. Pajerowski, S. Johnston, Z. Wang, H. Lane, Y. W. Li, X. Bai, M. Mourigal, C. D. Batista, K. Barros, Sunny.jl: A Julia package for spin dynamics, *arXiv/quant-ph:2501.13095*.
- [20] T. J. Williams, D. L. Abernathy, M. D. Lumsden, and A. D. Christianson, Measurements of CrSiTe_3 on HB3 and ARCS, Oak Ridge National Laboratory data repository (2026), doi: [10.14461/oncat.data/3230839](https://doi.org/10.14461/oncat.data/3230839).